



#### Researcher

Dr. Lawrence Sutter, Ph.D.  
Professor  
Michigan Tech  
Transportation Institute

lsutter@mtu.edu  
906.487.2268

#### Sponsor

University Transportation  
Center for Materials in Sus-  
tainable Transportation Infra-  
structure (UTC-MiSTI)

#### Project Title

Identifying the Fundamental  
Mechanisms of Potassium  
Acetate Deicer on Runways

#### Project Manager

Elizabeth Hoy  
Assistant Director, UTC-MiSTI

#### Co-Investigators

*Michigan Technological University*  
Dr. Karl Peterson, Ph.D.  
Research Assistant Professor  
Department of Civil and Envi-  
ronmental Engineering

Jerry Anzalone  
Graduate Research Assistant

Emily Van Dam  
Undergraduate Research  
Assistant

## Project Summary

Technology Transfer Outreach Publication

# Identifying the Fundamental Mechanisms of Potassium Acetate Deicer on Runways

Potassium acetate (KAc) is a chemical applied to the surface of airport runways to inhibit the formation of ice (anti-icing agent) or melt ice already formed (deicing agent). It became widely used in the early 1990's after discovering the high environmental cost of glycol-based deicers. It has since become the predominant anti/deicing agent in use on runways in the USA, but has been associated with premature distress and failure of portland cement concrete at a few airports across the country.

The observed distress appears to be alkali-silica reactivity (ASR) of aggregates, with map cracking visible on the pavement surface and a loss of physical integrity throughout the structure. ASR only occurs if there is "reactive" silica aggregate in the concrete, a source of hydroxyl (OH<sup>-</sup>) anions, and water present in the concrete. Reactive aggregates are amorphous, cryptocrystalline or poorly crystalline silica species such as opal or chert. Hydroxyl ions are supplied by portlandite (Ca(OH)<sub>2</sub>), a mineral compound that forms as portland cement hydrates and is therefore included in the hardened cement paste matrix. Water is supplied by the environment in which the pavement is placed.

The basic chemistry of the ASR distress process is relatively well understood whereas the mechanism leading to cracking is less well understood. The first step in the chemistry of the process – the dissolution of silica – is the focus of this research. The acetate anion is a carboxylate and is known to enhance the dissolution of minerals, silica included. In fact, carboxylates are widely used in water treatment regimes to control silica deposition in process water circuits. In particular, acetate solutions are used to dissolve colloidal silica that has precipitated on the surface of process water systems.

# Project Summary

Technology Transfer Outreach Publication



## University Facts (2008-2009)

Total Enrollment	7018
Graduate Enrollment	984
Number of Faculty	445
Placement Rate	96%

*Michigan Technological University is located in Houghton, Michigan on the south shore of Lake Superior. This rural area is known for natural beauty, pleasant summers, abundant snowfall, and numerous all-season outdoor activities. In addition, the University maintains its own downhill and cross-country ski facilities and golf course. There are numerous cultural activities and opportunities on campus and in the community. Michigan Tech has also been rated as one of the safest college campuses in the United States, and the local community provides excellent resources conducive to an outstanding quality of life.*

For more information, visit the University's website.

[www.mtu.edu](http://www.mtu.edu)

## Research Objective

- Determine the effect KAc has on the solubility of reactive silica aggregates.
- Determine the potential for paste alteration from KAc exposure.

## Methodology

A series of experiments will be conducted in which neat cement paste will be exposed to potassium acetate solutions and compared to pastes exposed to sodium hydroxide and plain water. A parallel series of experiments will investigate the relative solubility of silica in potassium acetate and sodium hydroxide. Both the solution and solids will be characterized upon completion of each experiment to determine the relative effect of potassium acetate on the aggregates and cement pastes.

*This publication was produced by the U.S. Department of Transportation University Transportation Center for Materials in Sustainable Transportation Infrastructure (UTC-MiSTI) at Michigan Technological University under the program management of the Office of Research and Technology Administration-U.S. Department of Transportation. The contents of this summary reflect the views of the authors, who are responsible for facts and the accuracy of the information presented herein. This document is disseminated under the sponsorship of the Department of Transportation University Transportation Centers program in the interest of information exchange. The U.S. Government assumes no liability for the contents or use thereof. For more information or additional copies, visit the Center's Web site at [www.misti.mtu.edu](http://www.misti.mtu.edu), call 906.487.3154, or write to UTC-MiSTI, 301 Dillman Hall, Michigan Technological University, 1400 Townsend Drive, Houghton, MI 49931*